



UNI EN ISO 9001:2008
Quality System Certified Company



TECHNICAL DATA SHEET PRODUCT

EPOXY 2+1 FLUID

TRANSPARENT EPOXY ADHESIVE OF MEDIUM HARDENING TIME for CONSOLIDATING and RESTRUCTURING MICROCRACKS and MICROSLITS

Two-component epoxy adhesive, transparent. Formulated for the consolidating and restructuring of micro-cracks of any type of marble, granite, natural and artificial stone, ceramics. Its negligible shrinkage allows the repair of deep cracks. Formulation of slow hardening time for deeper penetration.

FIELDS OF USE

For all types of stone and ceramic materials, both natural and synthetic,

PROPERTIES

- Excellent adhesion
- High transparency
- Weather and acid rain resistant
- Resistant to solvents, basic (therefore suitable to concrete) and acid environment
- Negligible yellowing
- High stability to UV rays
- Almost no shrinkage
- Practically odourless
- Also suitable for application of fiberglass net for reinforcing the materials.

WARNING

- Avoid the use at temperatures below 10°C/50°F
- It doesn't adhere to silicon
- It doesn't adhere to polyethylene

HOW TO USE

PREPARING THE SURFACE. Carefully clean the surfaces by removing any dust and loose parts, traces of cement, plaster, oil or fats, etc. Better adhesion if the support is slightly roughened.

PREPARING THE MIXTURE. Mix thoroughly component A and component B exactly in the ratio indicated A: B = 100: 50 until the complete homogenization.

APPLICATION. Apply the mixed product on the clean and dry surface with a spatula / putty knife.

After 8 to 12 hours it is possible the displacement of the piece and after 24-48 hours (depending on environment condition, temperature, humidity, etc.) you can proceed to subsequent processes.

IMPORTANT

- Do not use the mixture A + B if already in the process of gelation
- Do not return the unused product in the can/ container
- Store at temperatures between 10°C and 30°C / 50°F and 86°F
- The hardening is more rapid at higher temperatures and slower at low temperatures

MIXING RATIO

Component A : Component B = 100 : 50



PACKAGING

Set A+B 1,50 kg. (Component A = kg. 1,00 - Component B = kg. 0,50)
Set A+B 15,00 kg. (Component A = kg. 10,00 - Component B = kg. 5,00)

STABILITY

When kept in its original can sealed and intact, and stored in a dry place at temperature of 15°C-25°C/ 59°F-77°F, the product remains stable at least 12 months.

TECHNICAL DATA

	component A	component B
Physical state	liquid	liquid
Color	transparent	transparent
Odor	characteristic (slight)	characteristic (slight)
Density at 20°C/68°F	1,08 ± 0,05 g/cm ³	0,98 ± 0,05 g/cm ³
Viscosity at 25°C/77°F	900 - 1150 cPs	50 - 80 cPs
Toxicity	irritant	corrosive
Flammability	no	no

DATA REFERRED TO THE MIXTURE A+B

Catalysis ratio	A : B = 100 : 50
Appearance of the texture	viscous liquid
Time of workability (A=200 g. + B=100 g.)	15 - 20 minutes at 20°C /68°F
Rectivity time in thin layer (superficial hardening)	3 to 4 hours (at 25°C/77°F) 1 to 2 hours (at 40°C/104°F)
Viscosity of the mixture	450 - 600 cPs
Piece handling time (after application at room temp. 25°C/77°F)	8 to 10 hours
Piece processing start time	after 24 to 48 hours

LIMITATION OF LIABILITY The data provided derive from published information or from our own laboratory tests. The information provided here must be considered as a guideline and not as any form of performance guarantee. Liability for defective products, when verified, is limited to refund of the purchase price since application of the product is beyond the control of the manufacturer or supplier.

TESTING A SMALL, HIDDEN, AREA IS RECOMMENDED BEFORE THE APPLICATION